QC ABSTRACT

NAME OF WORK: Package No.03 (Package Consists of 21 Works)

L NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	KERB	Core Compressive strength	One Test		1	1
		Corrected Cylinder Compressive strength	One Test		1	1
		Equivalent Cube Compressive strength	One Test		1	1
7	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
8	Precast (250mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1

Assistant Executive Engineer
Kothanur Sub Division
BBMP, Bangalore

9	RCC(M20)	Compressive Strength(7days and 28days)	7 set /150-200 cum	179	14	14
10	GSB	SIEVE ANALYSIS	One Test		1	1
11	WMM	Sieve Analysis	One Test		1	1
		Impact Value	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
12	DBM	SIEVE ANALYSIS	One Test		1	1
		STRIPPING VALUE	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		IMPACT VALUE	One Test		1	1
		Specific gravity	One Test		1	1
		Water Absorption	One Test		1	1
		Marshal Stability	One Test		1	1
		Marshal flow	One Test		1	1
		Percent air Voids	One Test		1	1
		Percent Voids in mineral Aggregate	One Test		1	1
		Percent Voids filled with Bitumen	One Test		1	1
		Density	One Test		1	1
		Gradation	One Test		1	1
13	BC	SIEVE ANALYSIS	One Test		1	1
		STRIPPING VALUE	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		IMPACT VALUE	One Test		1	1
		Specific gravity	One Test		1	1
		Water Absorption	One Test		1	1
		Marshal Stability	One Test		1	1
		Marshal flow	One Test		1	1
		Percent air Voids	One Test		1	1
		Percent Voids in mineral	One Test		1	1
		Percent Voids filled with Bitumen	One Test		1	1
		Density	One Test		1	1
		Gradation	One Test		1	1
14	BITUMEN	Ductility	One Test		1	1
		Softening Point	One Test		1	1
		Penetration	One Test		1	1
		Flash Point	One Test		1	1
		Fire Point	One Test		1	1
15	TACK COAT	Rate of spread,	One Test		1	1

Assistant Executive Engineer
Kothanur Sub Division
BBMP, Bangalore

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2021-02-03-03** **Date: 05-12-20**
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	02-12-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1983 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	03-12-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.98	–
2	Finess by Air permeablity method (m^2/kg,Min)	297.3	225m^2/kg, Min
3	Density (gm/cc)	3.11	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	175 minutes	Not less than 30 minutes
6	Final Setting time	285 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2021-02-03-03 **Date: 31-12-20**
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	02-12-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	03-12-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.0N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.5N/mm2	Not less than 37 N/mm^2
3	28 Days	55.5N/mm^2	Not less than 53 N/mm^2

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2021-02-03-03** **Date: 05-12-20**
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	02-12-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	02-12-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	214	214	1.4	98.6	90-100
3	20 mm	5049	5263	35.1	64.9	30-70
4	10 mm	7132	12395	82.6	17.4	10-35
5	4.75 mm	2121	14516	96.8	3.2	0-5
6	Pan	484	15000	100.0	0	---

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2021-02-03-03** **Date: 05-12-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.9	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.1	
3	Specific Gravity	2.59	_
4	Bulk Density(Loose) (Kg/l)	1.39	_
5	Bulk Density(Compacted) (Kg/l)	1.46	_
6	Water Absorption(%)	0.22	_

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2021-02-03-03** **Date: 04-12-20**
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	02-12-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	02-12-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	195	195	3.9	96.1	90-100
3	10 mm	2714	2909	58.2	41.8	25-55
4	4.75 mm	1988	4897	97.9	2.1	0-10
5	Pan	103	5000	100	0	–

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2021-02-03-03** **Date: 04-12-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.8	
3	Specific Gravity	2.57	–
4	Bulk Density(Loose) (Kg/l)	1.41	–
5	Bulk Density(Compacted) (Kg/l)	1.49	–
6	Water Absorption(%)	0.28	–
7	Aggregate crushing Value(%)	23.1	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	21.7	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : CP-2021-02-03-03 **Date: 04-12-20**

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 02-12-20

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 02-12-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2021-02-03-03**

Date: 04-12-20

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	CP-2021-02-03-03
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	02-12-20
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	02-12-20

Date: 03-12-20

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	16	1.581	572	674	19.0%	Satisfactory	Satisfactory

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

ıb ID : CP-2021-02-03-03 **Date: 02-01-21**

oject Name : Package No.03 (Package Consists of 21 Works)

ɡency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

ıstomer's Reference : BBMP/EE/BTP/WO/148/2018-19

ıte of Receipt : 29-12-20

mple Type /Size : Precast Cover Slab (100mm)

ference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

te of test : 29/12/2020

l. o.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
	Cover Slab-1	75.51	100.48	1.116	4477	80.9	18.1	16.8	21.0
	Cover Slab-2	75.49	100.52	1.122	4475	82.3	18.4	17.1	21.4
	Cover Slab-3	75.50	100.51	1.118	4476	81.5	18.2	16.9	21.2

ıe results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF PRECAST COVER SLAB

Format No: CP/TF/01

ID	:	CP-2021-02-03-03
ject Name	:	Package No.03 (Package Consists of 21 Works)
ncy	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
tomer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
e of Receipt	:	29-12-20
ıple Type /Size	:	Precast Cover Slab (250mm)
rence to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
e of test	:	29/12/2020

Date: 02-01-21

	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
	Cover Slab-1	200.51	250.48	3.116	31570	230.9	7.3	6.8	8.5
	Cover Slab-2	200.49	250.52	3.122	31564	232.3	7.4	6.8	8.6
	Cover Slab-3	200.50	250.51	3.118	31567	231.5	7.3	6.8	8.5

e results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2021-02-03-03 Date: 22/12/2020

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 17-12-20

Customer ID : Drain Bottom Slab Concrete, (Arali Katte Opposite (LV Bekary Near Kodigehalli Circle))

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	15/12/2020	22/12/2020	151.26 X 149.21 X 151.89	22570	8.766	409.9	18.2	18.4
2	Drain Bottom Slab Concrete	M20	15/12/2020	22/12/2020	151.96 X 149.24 X 151.44	22679	8.338	416.9	18.4	
3	Drain Bottom Slab Concrete	M20	15/12/2020	22/12/2020	149.09 X 149.74 X 149.17	22324	8.979	417.3	18.7	

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2021-02-03-03 Date: 12/01/2021

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 17-12-20

Customer ID : Drain Bottom Slab Concrete, (Arali Katte Opposite (LV Bekary Near Kodigehalli Circle))

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	15/12/2020	12/01/2021	150.06 X 151.07 X 151.04	22668	8.659	541.0	23.9	
2	Drain Bottom Slab Concrete	M20	15/12/2020	12/01/2021	150.78 X 149.26 X 149.73	22506	8.245	510.8	22.7	23.2
3	Drain Bottom Slab Concrete	M20	15/12/2020	12/01/2021	151.27 X 149.97 X 151.81	22686	8.097	523.4	23.1	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2021-02-03-03 Date: 22/12/2020

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 17-12-20

Customer ID : Drain Bottom Slab Concrete, (Swd Drain To Kodigehalli Circle)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	15/12/2020	22/12/2020	149.62 X 151.49 X 150.34	22666	8.766	421.7	18.6	18.7
2	Drain Bottom Slab Concrete	M20	15/12/2020	22/12/2020	149.32 X 150.69 X 150.70	22501	8.338	422.8	18.8	
3	Drain Bottom Slab Concrete	M20	15/12/2020	22/12/2020	150.34 X 150.17 X 151.01	22577	8.979	423.8	18.8	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2021-02-03-03 Date: 12/01/2021

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 17-12-20

Customer ID : Drain Bottom Slab Concrete, (Swd Drain To Kodigehalli Circle)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	15/12/2020	12/01/2021	150.92 X 149.53 X 150.32	22567	8.659	526.9	23.4	23.2
2	Drain Bottom Slab Concrete	M20	15/12/2020	12/01/2021	150.99 X 149.34 X 149.06	22548	8.245	517.1	22.9	
3	Drain Bottom Slab Concrete	M20	15/12/2020	12/01/2021	149.46 X 149.48 X 149.11	22342	8.097	518.9	23.2	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

ab ID : CP-2021-02-03-03

Date: 26/12/2020

roject Name : Package No.03 (Package Consists of 21 Works)

gency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

ustomer's Reference : BBMP/EE/BTP/WO/148/2018-19

ate of Receipt : 21-12-20

ustomer ID : Drain Side Wall Concrete, (Arali Katte Opposite (LV Bekary Near Kodigehalli Circle))

ample Type /Size : 150X150X150 mm

ample grade/Age : M20 / 7 Days Compressive Strength

eference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

ate of test : 26/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	19/12/2020	26/12/2020	151.20 X 150.96 X 150.77	22825	8.766	427.9	18.7	18.7
2	Drain Side Wall Concrete	M20	19/12/2020	26/12/2020	150.00 X 149.28 X 149.21	22392	8.338	422.4	18.9	
3	Drain Side Wall Concrete	M20	19/12/2020	26/12/2020	150.81 X 150.11 X 151.72	22639	8.979	419.5	18.5	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2021-02-03-03

Date: 16/01/2021

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 21-12-20

Customer ID : Drain Side Wall Concrete, (Arali Katte Opposite (LV Bekary Near Kodigehalli Circle))

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	19/12/2020	16/01/2021	149.24 X 150.13 X 151.17	22405	8.659	536.2	23.9	23.5
2	Drain Side Wall Concrete	M20	19/12/2020	16/01/2021	151.73 X 151.53 X 150.77	22992	8.245	522.2	22.7	
3	Drain Side Wall Concrete	M20	19/12/2020	16/01/2021	151.73 X 151.62 X 151.81	23006	8.097	549.8	23.9	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

ab ID : CP-2021-02-03-03

roject Name : Package No.03 (Package Consists of 21 Works) **Date: 26/12/2020**

gency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

ustomer's Reference : BBMP/EE/BTP/WO/148/2018-19

ate of Receipt : 21-12-20

ustomer ID : Drain Side Wall Concrete, (Swd Drain To Kodigehalli Circle)

mple Type /Size : 150X150X150 mm

mple grade/Age : M20 / 7 Days Compressive Strength

ference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

te of test : 26/12/2020

il. lo.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	19/12/2020	26/12/2020	150.95 X 150.59 X 149.47	22731	8.766	412.2	18.1	18.3
2	Drain Side Wall Concrete	M20	19/12/2020	26/12/2020	150.64 X 150.12 X 149.49	22614	8.338	409.5	18.1	
3	Drain Side Wall Concrete	M20	19/12/2020	26/12/2020	149.43 X 150.42 X 150.63	22477	8.979	417.4	18.6	

he results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2021-02-03-03 Date: 16/01/2021

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 21-12-20

Customer ID : Drain Side Wall Concrete, (Swd Drain To Kodigehalli Circle)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	19/12/2020	16/01/2021	151.02 X 150.69 X 150.92	22757	8.659	532.1	23.4	23.2
2	Drain Side Wall Concrete	M20	19/12/2020	16/01/2021	149.50 X 149.68 X 150.30	22378	8.245	503.3	22.5	
3	Drain Side Wall Concrete	M20	19/12/2020	16/01/2021	149.10 X 151.78 X 149.34	22631	8.097	538.8	23.8	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

ab ID : CP-2021-02-03-03

roject Name : Package No.03 (Package Consists of 21 Works) Date: 28/12/2020

gency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

ustomer's Reference : BBMP/EE/BTP/WO/148/2018-19

ate of Receipt : 23-12-20

ustomer ID : Culvert Bottom Slab Concrete, (Under Pass to SWD Drain)

mple Type /Size : 150X150X150 mm

mple grade/Age : M20 / 7 Days Compressive Strength

eference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

ate of test : 28/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Botttom Slab Concrete	M20	21/12/2020	28/12/2020	150.48 X 149.83 X 151.85	22546	8.766	425.7	18.9	18.5
2	Culvert Botttom Slab Concrete	M20	21/12/2020	28/12/2020	151.63 X 149.78 X 151.61	22711	8.338	409.3	18.0	
3	Culvert Botttom Slab Concrete	M20	21/12/2020	28/12/2020	151.17 X 149.09 X 151.38	22539	8.979	418.7	18.6	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/01/2021

Lab ID : CP-2021-02-03-03

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 23-12-20

Customer ID : Culvert Bottom Slab Concrete, (Under Pass to SWD Drain)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Botttom Slab Concrete	M20	21/12/2020	18/01/2021	150.42 X 150.57 X 151.09	22649	8.659	524.1	23.1	23.1
2	Culvert Botttom Slab Concrete	M20	21/12/2020	18/01/2021	150.75 X 151.28 X 151.88	22806	8.245	504.5	22.1	
3	Culvert Botttom Slab Concrete	M20	21/12/2020	18/01/2021	149.93 X 151.89 X 149.33	22772	8.097	545.1	23.9	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

b ID	:	CP-2021-02-03-03 **Date: 31/12/2020**
oject Name	:	Package No.03 (Package Consists of 21 Works)
ency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
stomer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
te of Receipt	:	26-12-20
stomer ID	:	Culvert Side Wall Concrete, (Under Pass to SWD Drain)
mple Type /Size	:	150X150X150 mm
mple grade/Age	:	M20 / 7 Days Compressive Strength
ference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
te of test	:	31/12/2020

l. o.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	Culvert SideWall Concrete	M20	24/12/2020	31/12/2020	150.50 X 150.31 X 149.81	22622	8.766	428.7	19.0	18.7
	Culvert SideWall Concrete	M20	24/12/2020	31/12/2020	149.88 X 150.94 X 149.20	22623	8.338	423.1	18.7	
	Culvert SideWall Concrete	M20	24/12/2020	31/12/2020	151.09 X 151.23 X 151.03	22849	8.979	420.8	18.4	

he results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

ab ID : CP-2021-02-03-03

Date: 21/01/2021

roject Name : Package No.03 (Package Consists of 21 Works)

gency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

ustomer's Reference : BBMP/EE/BTP/WO/148/2018-19

ate of Receipt : 26-12-20

ustomer ID : Culvert Side Wall Concrete, (Under Pass to SWD Drain)

ample Type /Size : 150X150X150 mm

ample grade/Age : M20 / 28 Days Compressive Strength

eference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

ate of test : 21/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Side wall Concrete	M20	24/12/2020	21/01/2021	149.66 X 149.75 X 151.49	22411	8.659	533.1	23.8	23.4
2	Culvert Side wall Concrete	M20	24/12/2020	21/01/2021	150.02 X 150.35 X 151.48	22556	8.245	507.3	22.5	
3	Culvert Side wall Concrete	M20	24/12/2020	21/01/2021	150.84 X 151.74 X 149.12	22888	8.097	547.4	23.9	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

DR KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : CP-2021-02-03-03

Project Name : Package No.03 (Package Consists of 21 Works) **Date: 31/12/2020**

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 26-12-20

Customer ID : Culvert Side Wall Concrete, (SWD Drain to Kodigehalli Circle)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert SideWall Concrete	M20	24/12/2020	31/12/2020	151.85 X 151.49 X 151.01	23004	8.766	427.4	18.6	18.5
2	Culvert SideWall Concrete	M20	24/12/2020	31/12/2020	150.45 X 150.31 X 150.68	22614	8.338	417.0	18.4	
3	Culvert SideWall Concrete	M20	24/12/2020	31/12/2020	150.66 X 149.49 X 150.99	22522	8.979	416.3	18.5	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY ANABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No: TC-8568

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CPTP/01

Lot ID : CP-2021-02-03-03

Project Name : Package No.03 (Package Consists of 21 Works) Date: 21/01/2021

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043

Customer's Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 26-12-20

Customer ID : Culvert Side Wall Concrete, (SWD Drain to Kodigehalli Circle)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 21/01/2021

Sl No	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	Culvert SideWall Concrete	M20	24/12/2020	21/01/2021	151.96 X 150.70 X 151.72	22900	8.659	546.4	23.9	23.2
2	Culvert SideWall Concrete	M20	24/12/2020	21/01/2021	150.61 X 150.54 X 150.40	22674	8.245	517.2	22.8	
3	Culvert SideWall Concrete	M20	24/12/2020	21/01/2021	151.25 X 151.22 X 151.29	22872	8.097	526.9	23.0	

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

B.KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST RESULTS OF GRADATION FOR GSB
(IS 2386:(Part 1) 1963 (RA2011)

Lab ID : **CP-RW-2021-02-03-03**

Project Name : Package No.03 (Package Consists of 21 Works) **Date: 10-12-20**

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 08-12-20

Type of Mix : GSB (Granular Sub Base)

Date of test : 08-12-20

Oven Dry Weight : 10000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec. Limit Vide Table 400.1 MORTH Specification
75	0	0	0	100	100
53	997	997	9.97	90.03	80-100
26.5	1685	2682	26.82	73.18	55-90
9.5	1292	3974	39.74	60.26	35-65
4.75	1490	5464	54.64	45.36	25-55
2.36	1764	7228	72.28	27.72	20-40
0.425	1666	8894	88.94	11.06	10-25
0.075	1106	10000	100.00	0.00	0-5

TESTS ON FILLER SCREEN MATERIALS

Sl no	Particulars	Test results	Spec.Limit Vide Table
1	Liquid Limit, %	21.33%	Maximum 25
2	Plasticity index, %	Non plastic	Maximum 6

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST RESULTS OF GRADATION FOR GSB
(IS 2386:(Part 1) 1963 (RA2011)

Lab ID : CP-RW-2021-02-03-03 Date: 11-12-20

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 09-12-20

Type of Mix : GSB (Granular Sub Base)

Date of test : 09-12-20

Oven Dry Weight : 10000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec. Limit Vide Table 400.1 MORTH Specification
75	0	0	0	100	100
53	997	997	9.97	90.03	80-100
26.5	1685	2682	26.82	73.18	55-90
9.5	1292	3974	39.74	60.26	35-65
4.75	1490	5464	54.64	45.36	25-55
2.36	1764	7228	72.28	27.72	20-40
0.425	1666	8894	88.94	11.06	10-25
0.075	1106	10000	100.00	0.00	0-5

TESTS ON FILLER SCREEN MATERIALS

Sl no	Particulars	Test results	Spec.Limit Vide Table
1	Liquid Limit, %	21.33%	Maximum 25
2	Plasticity index, %	Non plastic	Maximum 6

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

TEST RESULTS OF GRADATION FOR GSB
(IS 2386:(Part 1) 1963 (RA2011)

Lab ID	:	CP-RW-2021-02-03-03	Date: 12-12-20
Project Name	:	Package No.03 (Package Consists of 21 Works)	
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.	
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19	
Date of Receipt	:	10-12-20	
Type of Mix	:	GSB (Granular Sub Base)	
Date of test	:	10-12-20	
Oven Dry Weight	:	10000	Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec. Limit Vide Table 400.1 MORTH Specification
75	0	0	0	100	100
53	997	997	9.97	90.03	80-100
26.5	1685	2682	26.82	73.18	55-90
9.5	1292	3974	39.74	60.26	35-65
4.75	1490	5464	54.64	45.36	25-55
2.36	1764	7228	72.28	27.72	20-40
0.425	1666	8894	88.94	11.06	10-25
0.075	1106	10000	100.00	0.00	0-5

TESTS ON FILLER SCREEN MATERIALS

Sl no	Particulars	Test results	Spec.Limit Vide Table
1	Liquid Limit, %	21.33%	Maximum 25
2	Plasticity index, %	Non plastic	Maximum 6

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST RESULTS OF GRADATION FOR WMM

Lab ID : CP-RW-2021-02-03-03 Date: 12-12-20

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 10-12-20

Type of Mix : WMM (Wet Mix Macadam)

Date of test : 10-12-20

Oven Dry Weight : 11000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	315	315	2.9	97.1	95-100
22.4	2259	2574	23.4	76.6	60-80
11.2	2179	4753	43.2	56.8	40-60
4.75	2251	7004	63.7	36.3	25-40
2.36	1621	8625	78.4	21.6	15-30
0.6	623	9248	84.1	15.9	8-22
0.075	1338	10586	96.2	3.8	0-5

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST RESULTS OF GRADATION FOR WMM

Lab ID	:	CP-RW-2021-02-03-03 Date: 14-12-20
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	11-12-20
Type of Mix	:	WMM (Wet Mix Macadam)
Date of test	:	11-12-20
Oven Dry Weight	:	11000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	315	315	2.9	97.1	95-100
22.4	2259	2574	23.4	76.6	60-80
11.2	2179	4753	43.2	56.8	40-60
4.75	2251	7004	63.7	36.3	25-40
2.36	1621	8625	78.4	21.6	15-30
0.6	623	9248	84.1	15.9	8-22
0.075	1338	10586	96.2	3.8	0-5

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST RESULTS OF GRADATION FOR WMM

Lab ID : CP-RW-2021-02-03-03 Date: 14-12-20

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 12-12-20

Type of Mix : WMM (Wet Mix Macadam)

Date of test : 12-12-20

Oven Dry Weight : 11000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	315	315	2.9	97.1	95-100
22.4	2259	2574	23.4	76.6	60-80
11.2	2179	4753	43.2	56.8	40-60
4.75	2251	7004	63.7	36.3	25-40
2.36	1621	8625	78.4	21.6	15-30
0.6	623	9248	84.1	15.9	8-22
0.075	1338	10586	96.2	3.8	0-5

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | MANAGEMENT | SURVEYING SERVICES |

TEST RESULTS OF GRADATION FOR WMM

Lab ID : CP-RW-2021-02-03-03 Date: 16-12-20

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 14-12-20

Type of Mix : WMM (Wet Mix Macadam)

Date of test : 14-12-20

Oven Dry Weight : 11000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	315	315	2.9	97.1	95-100
22.4	2259	2574	23.4	76.6	60-80
11.2	2179	4753	43.2	56.8	40-60
4.75	2251	7004	63.7	36.3	25-40
2.36	1621	8625	78.4	21.6	15-30
0.6	623	9248	84.1	15.9	8-22
0.075	1338	10586	96.2	3.8	0-5

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No : TC-5548

TEST REPORT OF AGGEGRATE IMPACT VALUE
IS: 2386 Part IV

Lab ID	:	CP-RW-2021-02-03-03	Date: 12-12-20
Project Name	:	Package No.03 (Package Consists of 21 Works)	
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.	
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19	
Date of Receipt	:	10-12-20	
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)	
Date of test	:	10-12-20	

Sl.No	Particulars of observations	Index	TEST 1	TEST 2
1	Total weight of the surface dry sample sample (passing 12.5 mm and retained on 10mm sieve)	A	300.2	300.2
2	Weight of fraction passing 2.36mm sieve After giving 15 blows	B	73.9	74.0
3	weight of fraction retained 2.36mm sieve After giving 15 blows	C	225.9	225.8
4	Total weight of (B+C) is less than the initial weight (Weight A) by more than one gram the result shall be discarded and a fresh test made.	A-(B+C)	0.4	0.4
5	Aggregate impact value	(B/A)*100	24.6	24.7
6	Aggregate impact value (Mean of two tests)	Pecentage	24.6	

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

DETERMINATION OF FLAKINESS INDEX AND ELONGATION INDEX OF COARSE AGGREGATE(IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	CP-RW-2021-02-03-03 **Date: 12-12-20**
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	10-12-20
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of test	:	10-12-20

Result:

Index	Percentage of Flakiness and Elongation Index	Secified limits as per MORTH specification table 400-12
Flakiness Index	12.8%	Combined Flakiness & Elongation Index for WMM is Maximum 35%
Elongation Index	12.5%	
Combined Flakiness and Elongation Index for WMM	25.3%	

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

DETERMINATION OF FLAKINESS INDEX AND ELONGATION INDEX OF COARSE AGGREGATE(IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	**CP-RW-2021-02-03-03**	**Date: 14-12-20**
Project Name	:	Package No.03 (Package Consists of 21 Works)	
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.	
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19	
Date of Receipt	:	11-12-20	
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)	
Date of test	:	11-12-20	

Result:

Index	Percentage of Flakiness and Elongation Index	Secified limits as per MORTH specification table 400-12
Flakiness Index	12.8%	Combined Flakiness & Elongation Index for WMM is Maximum 35%
Elongation Index	12.5%	
Combined Flakiness and Elongation Index for WMM	25.3%	

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT ON BITUMEN

Format No: CP/TF/01

Lab ID	:	CP-RW-2021-02-03-03
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer's Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	28-12-20
Sample Type	:	Bitumen
Reference to BIS codes	:	IS: 1201-1220(1978) (Reaffirmed-2004)
Date of test	:	28-12-20

Date: 30-12-20

Test Results

Sl.no	Name of Test	Result	Requirements as per IS:73-2013
1	Penetration at 25°C , in 1/10th mm	64	60 to 70
2	Softening Point, °C	51.2	Min. 40°C
3	Ductility, cm	98	Min. 75cm
4	Flash point, °C	245	Min. 220°C
	Fire point, °C	272	

* The results obtained are satisfactory as per standard requirements.

Assistant Executive ...
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST RESULTS OF GRADATION FOR DBM
(IS 2386:(Part 1) 1963 (RA2011)

Lab ID : CP-RW-2021-02-03-03

Date: 01-01-21

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 30-12-20

Type of Mix : DBM-Plant (Dense Bituminous Macadam)

Date of test : 30-12-20

Weight of Sample : 5000 Grams

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Specification Limits as per MORTH specification Table 500-10 (grading -2)
37.5	0	0	0	100	100
26.5	250	250	5.00	95.00	90-100
19	350	600	12.00	88.00	71-95
13.2	450	1050	21.00	79.00	56-80
4.75	1750	2800	56.00	44.00	38-54
2.36	400	3200	64.00	36.00	28-42
0.3	1350	4550	91.00	9.00	7-21
0.075	250	4800	96.00	4.00	2-8
PAN	200	5000	0.00	0	0

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

PHYSICAL REQUIREMENTS FOR COARSE AGGREGATE FOR DENSE BITUMINOUS MACADAM

Lab ID : **CP-RW-2021-02-03-03** **Date: 02-01-21**

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 30-12-20

Type of Mix : DBM (Dense Bituminous Macadam)

Date of test : 30-12-20

Table 500-6 : Physical Requirements fo Coarse Aggregate for Dense Bituminous Macadam

Property	Test	Result	Specification	Method of Test
Partical Shape	Flakiness Index	10.0	Combined Flakiness & Elongation Index for DBM is Maximum 35%	IS:2386 Part I
	Elongation Index	9.0		
Strength	Aggregate Impact Value	21.0	Maximum 30%	IS:2386 Part IV
Specific gravity	Specific gravity	2.58	Maximum 2.7	IS:2386 Part III
Water Absorption	Water Absorption	0.38	Maximum 2%	IS:2386 Part III

*The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kadigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quallity Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TESTS RESULTS ON STABILITY OF MIX

Lab ID : **CP-RW-2021-02-03-03** **Date: 02-01-21**

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 30-12-20

Type of Mix : DBM (Dense Bituminous Mecadam)

Date of test : 30-12-20

The results of the tests conducted on the Dense Bituminous Macadam mix sample are as follow

Sl.No	Particulars of observations	TEST 1	TEST 2	Secified limits as per MORTH specification table 500-11
1	Marshal Stability at 60°C, KN	11.29	11.82	9KN(Min)
2	Marshal flow at 60°C, mm	3.54	3.87	2-4
3	Percent air Voids	4.56	4.17	3-5
4	Percent Voids in mineral Aggregate(VMA %)	14.54	14.76	13-15
5	Percent Voids filled with Bitumen(VFB %)	68.98	70.28	65-75
6	Density, g/cc	2.42	2.40	–

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

TEST REPORT OF AGGEGRATE STRIPPING VALUE OF ROAD AGGRGATE (IS:6241)

Lab ID : CP-RW-2021-02-03-03 Date: 02-01-21

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 30-12-20

Type of Mix : DBM(Dense Bitumnous Macadam)

Date of test : 30-12-20

Type of Binder : 60/70

% of Binder Used : 5.0%

Weight of Aggregate : 200.0 gm

Weight of Binder : 10.0 gm

Temperature of water bath : 40°C

No of test	Retained Stripping Percentage	Stripping Percentage	Average Retained Stripping Percentage	Secified limits as per MORTH specification table 500-8
1	98.0	2.0	98.2	Minimum Retained Coating 95%
2	98.5	1.5		
3	98.0	2.0		

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kathigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST RESULTS OF BITUMEN BINDAR CONTENT AND GRADATION FOR DBM (IS 2386:(Part 1) 1963 (RA2011)

Lab ID : CP-RW-2021-02-03-03

Project Name : Package No.03 (Package Consists of 21 Works) **Date: 05-01-21**

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 04-01-21

Type of Mix : DBM (Dense Bituminous Macadam), (Under Pass to SWD Drain)

Date of test : 04-01-21

Sl.no	Description	Index	Trail 1	Trail 2
1	Weight of the Sample	A	500	500
2	Weight of the sample After extraction	B	475	476
3	Bitumen percentage	$\frac{A-B}{A} \times 100$	4.8	4.8
4	Average percentage	%	4.8	

Assistant Executive Engineer
Yelahanka Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Lab ID : CP-RW-2021-02-03-03 Date: 05-01-21

AFTER EXTRACTION(Trail-1)

Weight of Sample(gm) : 475

IS Sieve Size(mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Specification Limits as per MORTH specification Table 500-10(grading -2)
37.5	0	0	0	100.0	100
26.5	14.4	14.4	3.03	97.0	90-100
19	24	38.4	8.08	91.9	71-95
13.2	120	158.4	33.35	66.7	56-80
4.75	96	254.4	53.56	46.4	38-54
2.36	80	334.4	70.40	29.6	28-42
0.3	62.4	396.8	83.54	16.5	7-21
0.075	52.8	449.6	94.65	5.3	2-8

AFTER EXTRACTION(Trail-2)

Weight of Sample(gm) : 476

IS Sieve Size(mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Specification Limits as per MORTH specification Table 500-10(grading -2)
37.5	0	0	0	100.0	100
26.5	14.8	14.8	3.11	96.9	90-100
19	24	38.8	8.15	91.8	71-95
13.2	120	158.8	33.36	66.6	56-80
4.75	96	254.8	53.53	46.5	38-54
2.36	78	332.8	69.92	30.1	28-42
0.3	62.4	395.2	83.03	17.0	7-21
0.075	52.8	448	94.12	5.9	2-8

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engi...
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Certificate No.: TC-5548

TEST RESULTS OF GRADATION FOR BC
IS 2386 (Part 1) 1963 (RA 2007)

Lab ID : CP-RW-2021-02-03-03

Project Name : Package No.03 (Package Consists of 21 Works) **Date: 08-01-21**

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 06-01-21

Type of Mix : BC-Plant (Bituminous Concrete)

Date of test : 06-01-21

Oven Dry Weight : 5000 Grams

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-17(grading-2)
19	0	0	0.0	100.0	100
13.2	89	89	1.8	98.2	90-100
9.5	702	791	15.8	84.2	70-88
4.75	895	1686	33.7	66.3	53-71
2.36	587	2273	45.5	54.5	42-58
1.18	492	2765	55.3	44.7	34-48
0.6	503	3268	65.4	34.6	26-38
0.3	528	3796	75.9	24.1	18-28
0.15	458	4254	85.1	14.9	12-20
0.075	350	4604	92.1	7.9	4-10
PAN	396	5000	100	0.0	0

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF AGGEGRATE STRIPPING VALUE OF ROAD AGGRGATE (IS:6241)

Lab ID	:	**CP-RW-2021-02-03-03**	**Date: 09-01-21**
Project Name	:	Package No.03 (Package Consists of 21 Works)	
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.	
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19	
Date of Receipt	:	06-01-21	
Type of Mix	:	BC(Bitumenous Concrete)	
Date of test	:	06-01-21	

Type of Binder	:	60/70
% of Binder Used	:	5.0%
Weight of Aggregate	:	200.0 gm
Weight of Binder	:	10.0 gm
Temperature of water bath	:	40°C

No of test	Retained Stripping Percentage	Stripping Percentage	Average Retained Stripping Percentage	Secified limits as per MORTH specification table 500-8
1	98.5	1.5	98.3	Minimum Retained Coating 95%
2	98.5	1.5		
3	98.0	2.0		

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

PHYSICAL REQUIREMENTS FOR COARSE AGGREGATE FOR BITUMINOUS CONCRETE

Lab ID : CP-RW-2021-02-03-03 **Date: 09-01-21**

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 06-01-21

Type of Mix : BC (Bituminous Concrete)

Date of test : 06-01-21

Table 500-16 : Physical Requirements fo Coarse Aggregate for Bituminous Concrete

Property	Test	Result	Specification	Method of Test
Partical Shape	Flakiness Index	12.4	Combined Flakiness & Elongation Index for BC is Maximum 35%	IS:2386 Part I
	Elongation Index	11.8		
Strength	Aggregate Impact Value	22.1	Maximum 24%	IS:2386 Part IV
Specific gravity	Specific gravity	2.68	Maximum 2.7	IS:2386 Part III
Water Absorption	Water Absorption	0.21	Maximum 2%	IS:2386 Part III

The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quallity Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TESTS RESULTS ON STABILITY OF MIX

Lab ID : CP-RW-2021-02-03-03

Project Name : Package No.03 (Package Consists of 21 Works) Date: 09-01-21

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 06-01-21

Type of Mix : BC (Bituminous Concrete)

Date of test : 06-01-21

The results of the tests conducted on the Bituminous Concrete mix sample are as follow

Sl.No	Particulars of observations	TEST 1	TEST 2	Secified limits as per MORTH specification table 500-11
1	Marshal Stability at 60°C, KN	11.14	11.13	10KN(min)
2	Marshal flow at 60°C, mm	3.52	3.51	2-4
3	Percent air Voids	4.82	4.83	3-5
4	Percent Voids in mineral Aggregate(VMA %)	14.28	14.26	13-15
5	Percent Voids filled with Bitumen(VFB %)	71.87	71.63	65-75
6	Density, g/cc	2.25	2.26	–

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Yelahanka Sub Division

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M: 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

DETERMINATION OF RATE OF SPREAD TACK COAT

Lab ID	:	CP-RW-2021-02-03-03 **Date: 12-01-21**
Project Name	:	Package No.03 (Package Consists of 21 Works)
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19
Date of Receipt	:	11-01-21
Type of Mix	:	Tack coat
Date of test	:	11-01-21

Sl.No	Determination	Unit	TEST 1	TEST 2
1	Size of Plate (mxm)	Mt	0.30 x .30	0.30 x .30
2	Area of Plate (a)	Sq.mtr	0.09	0.09
3	Initial Wt of empty Plate (b)	Kg	0.78	0.748
4	Final weight of plate after application of tack Coat (c)	Kg	0.803	0.771
5	Weight of tack Coat (d=c-b)	Kg	0.023	0.023
6	Rate of spread of tack coat	Kg/sq.m	0.256	0.256
7	Average	Kg/sq.m	0.256	
8	Specified Limit	Kg/sq.m	0.250 Kg/sq.m	

* The results obtained are satisfactory as per standard requirements

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.
R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
End of Report

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

TEST RESULTS OF BITUMEN BINDAR CONTENT AND GRADATION FOR BC
IS 2386 (Part 1) 1963 (RA 2011)

Lab ID	:	**CP-RW-2021-02-03-03**	**Date: 12-01-21**
Project Name	:	Package No.03 (Package Consists of 21 Works)	
Agency	:	Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.	
Customer Reference	:	BBMP/EE/BTP/WO/148/2018-19	
Date of Receipt	:	11-01-21	
Type of Mix	:	BC (Bituminous Concrete), (Under Pass to SWD Drain)	
Date of test	:	11-01-21	

Sl.no	Description	Index	Trail 1	Trail 2
1	Weight of the Sample	A	500	500
2	Weight of the sample After extraction	B	472	471
3	Bitumen percentage	$\frac{A-B}{A} \times 100$	5.60	5.80
4	Average percentage	%	5.7	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Assistant Executive Engineer
Kodigehalli Sub Division
BBMP, Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Lab ID : CP-RW-2021-02-03-03 Date: 12-01-21

AFTER EXTRACTION - Trail-1

Total Weight of the Sample(gm) : 472

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-23(grading-2)
19	0	0	0.0	100.0	100
13.2	4	4	0.8	99.2	90-100
9.5	62	66	14.0	86.0	70-88
4.75	112	178	37.7	62.3	53-71
2.36	88	266	56.4	43.6	42-58
1.18	29	295	62.5	37.5	34-48
0.6	11	306	64.8	35.2	26-38
0.3	46	352	74.6	25.4	18-28
0.15	45	397	84.1	15.9	12-20
0.075	55	452	95.8	4.2	4-10

AFTER EXTRACTION - Trail-2

Total Weight of the Sample(gm) : 471

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-23(grading-2)
19	0	0	0.0	100.0	100
13.2	4	4	0.8	99.2	90-100
9.5	62	66	14.0	86.0	70-88
4.75	112	178	37.8	62.2	53-71
2.36	88	266	56.5	43.5	42-58
1.18	29	295	62.6	37.4	34-48
0.6	11	306	65.0	35.0	26-38
0.3	46	352	74.7	25.3	18-28
0.15	45	397	84.3	15.7	12-20
0.075	55	452	96.0	4.0	4-10

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engine
Kodigehalli Sub Division
BBMP, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

B KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

TEST RESULTS OF BITUMEN BINDAR CONTENT AND GRADATION FOR BC
IS 2386 (Part 1) 1963 (RA 2011)

Lab ID : CP-RW-2021-02-03-03 **Date: 12-01-21**

Project Name : Package No.03 (Package Consists of 21 Works)

Agency : Sri.C.G.Chandrappa, #1C-301, 3rd Main Block, HRBR Layout, Kalyan Nagar, Bangalore-560043.

Customer Reference : BBMP/EE/BTP/WO/148/2018-19

Date of Receipt : 11-01-21

Type of Mix : BC (Bituminous Concrete), (Tata nagar, 5th Cross Road)

Date of test : 11-01-21

Sl.no	Description	Index	Trail 1	Trail 2
1	Weight of the Sample	A	500	500
2	Weight of the sample After extraction	B	472	471
3	Bitumen percentage	$\frac{A-B}{A} \times 100$	5.60	5.80
4	Average percentage	%	5.7	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Assistant Executive Engineer
Kathriguppe Sub Division
BBMP, Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Certificate No.: TC-5548

Lab ID : CP-RW-2021-02-03-03

Date: 12-01-21

AFTER EXTRACTION - Trail-1

Total Weight of the Sample(gm) : 472

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-23(grading-2)
19	0	0	0.0	100.0	100
13.2	4	4	0.8	99.2	90-100
9.5	62	66	14.0	86.0	70-88
4.75	112	178	37.7	62.3	53-71
2.36	88	266	56.4	43.6	42-58
1.18	29	295	62.5	37.5	34-48
0.6	11	306	64.8	35.2	26-38
0.3	46	352	74.6	25.4	18-28
0.15	45	397	84.1	15.9	12-20
0.075	55	452	95.8	4.2	4-10

AFTER EXTRACTION - Trail-2

Total Weight of the Sample(gm) : 471

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-23(grading-2)
19	0	0	0.0	100.0	100
13.2	4	4	0.8	99.2	90-100
9.5	62	66	14.0	86.0	70-88
4.75	112	178	37.8	62.2	53-71
2.36	88	266	56.5	43.5	42-58
1.18	29	295	62.6	37.4	34-48
0.6	11	306	65.0	35.0	26-38
0.3	46	352	74.7	25.3	18-28
0.15	45	397	84.3	15.7	12-20
0.075	55	452	96.0	4.0	4-10

* The results obtained are satisfactory as per standard requirements.

Assistant Executive Engineer
Karnataka Slum Development Board, Bangalore

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |